

FROHN

Steel Cut-Wire for shot blasting



Application

Blast cleaning, descaling, rust removal, abrasive blasting, blast cutting, deburring or roughing

Manufacturing standards / Applicable Specifications


DIN 8201-4:1985

Sizes in mm (inch)

0,4 (.017)	0,7 (.028)	1,2 (.047)	1,8 (.070)
0,5 (.020)	0,8 (.032)	1,4 (.054)	2,0 (.078)
0,6 (.023)	0,9 (.035)	1,6 (.062)	

Other sizes available upon request

Grain shape



cylindrical (CW)

Material Hardness

400 HV_{0,5/1} – 500 HV_{0,5/1}

Other hardness ranges available upon request

Packaging

- 25 kg PE plastic bags on European pallet up to 1000 kg
- Big Bags from 500 to 1000 kg on non-returnable pallet

Other packaging available upon request