

FROHN

Plastic Shot



Characteristics

High durability (High Resist), high ductility, peening without residues, no colour-contamination, constant grain shape and grain size

Application

Deburring of: Duroplast parts, Rubber parts, Silicone parts,
Elastomere plastics, Cast parts
Surface cleaning

Material

Polyamid PA 6 - 6.6 red

Other materials and colours available upon request

Sizes

0,75 mm x 0,75 mm

1,00 mm x 1,00 mm

1,50 mm x 1,50 mm

Other sizes available upon request

Grain shape

cubical or cylindrical



cubical

Material Hardness

ca. HRM 110 - 105

Specific weight

ca. 1,12-1,14 kg/l

Bulk density

ca. 0,68 kg/l

Packaging

- 25 kg plastic bags

Other packaging available upon request