

40-60 Size Corn Cob

Passing	Retained On	Particle Size Distribution		
U.S. Standard Screen #	U.S. Standard Screen #	Typical %	Min. %	Max. %
-	30	0	0	0
30	40	0.5		2
40	60	92		
60	80	7		
80	-	0.5	0	1
Bulk Density: 19 - 28 pounds per cubic foot				
Moisture: Not more than 10%				





4060 Grade is most often used as a “carrier” for animal health and nutrition products. However, it is the preferred blasting media for log homes when there is a desire for a smoother appearance to the grit-blasted logs than would be the case if 2040 was used.

