



CARBOREX[®] RA

General Inquiries
 Tel: 1-800-828-1666
 info@washingtomills.com
 www.washingtomills.com

Washington Mills North Grafton, Inc.
 PO Box 428
 20 North Main Street
 North Grafton, MA 01536
 Tel: 508-839-6511
 Fax: 508-839-7675
 Email: info@washingtomills.com

Washington Mills Electro Minerals Corp.
 PO Box 423
 1801 Buffalo Avenue
 Niagara Falls, NY 14302
 Tel: 716-278-6600
 Fax: 716-278-6650
 Email: info@washingtomills.com

Washington Mills Electro Minerals Corp.
 PO Box 1002
 7780 Stanley Avenue
 Niagara Falls, Ontario L2E 6V9 Canada
 Email: info@washingtomills.com

Washington Mills Tonawanda, Inc.
 1000 E. Niagara Street
 Tonawanda, NY 14150
 Email: info@washingtomills.com

Washington Mills Electro Minerals Ltd.
 Mosley Road, Trafford Park
 Manchester M17 1NR England
 Email: info@washingtomills.com

Washington Mills Hennepin, Inc.
 13230 ESK Street
 Hennepin, IL 61327
 Email: info@washingtomills.com

Washington Mills AS
 NO-7300
 Orkanger, Norway
 Email: wmas@washingtomills.no

DESCRIPTION

CARBOREX[®] RA is a black, semi-friable, medium density, virgin silicon carbide abrasive.

APPLICATIONS

CARBOREX[®] RA is used primarily for gear lapping, flat lapping of metals and ceramics, glass grinding, and granite polishing.

TYPICAL CHEMICAL ANALYSIS

SiC	97.80%
SiO ₂	0.60%
Si	0.80%
Fe	0.20%
Al	0.30%
C	0.30%

GRAIN SIZES AVAILABLE

6, 8, 10, 12, 14, 16, 20, 24, 30, 36, 46, 54, 60, 70, 80, 90, 100, 120, 150, 180, 220, and 240

POWDER SIZES AVAILABLE

240, 280, 320, 360, 400, 500, 600, 800, 1000, 1200, F, FF, and FFF

TYPICAL PHYSICAL PROPERTIES

Crystallography	Alpha silicon carbide in a hexagonal crystal
Color	Black
Specific Gravity	3.20
Knoop ₁₀₀ Hardness	2450
Shape	Blocky, with sharp edges
Ball Mill Friability	64 (14 grit)
Grading (Grain)	ANSI B74.12-2001, Table 2 OR FEPA 42-1:2006
Grading (Powder)	ANSI B74.10-2001 OR FEPA 42-2:2006
Bulk Density (Grain)	ANSI B74.4-1992 (R2007)

TYPICAL BULK DENSITY

Grit	g/cc	Grit	g/cc	Grit	g/cc	Grit	g/cc
6	1.48	20	1.55	60	1.49	150	1.41
8	1.49	24	1.54	70	1.48	180	1.39
10	1.50	30	1.53	80	1.46	220	1.38
12	1.55	36	1.53	90	1.45		
14	1.55	46	1.52	100	1.44		
16	1.56	54	1.51	120	1.43		

This product information is NOT a specification. It is offered in good faith only as a general description of the product. **Washington Mills makes no warranty of merchantability or of fitness for any particular purpose.** The product chemistry and other characteristics may vary or contain trace elements not specifically listed. If your intended application for this product is so critical that relatively minor variations in chemistry or physical properties could cause problems or damage to your process or product, please contact our office for further assistance.